

SMI, Inc.

12219 SW 131 Avenue
Miami, Florida 33186-6401 USA

Phone: (305) 971-7047
Fax: (305) 971-7048

Attn: David Wooldridge
Chemetall
Denbigh Road; Bletchley
Milton Keynes
MK1 1PB ENGLAND

Date: 03-Feb-1999

SMI/REF: 9901081-BR
Reissued for name change only.

Product: **ARDROX 2814** (received 29-Jan-1999)

Dilution: Per specification

Page 1 of 1

Partial Testing in Accordance with **Mil-R-81903A** Amendment 2 16-Apr-1985
**REMOVER, ACID ACTIVATED, FOR AMINE-CURED
EPOXY COATING SYSTEMS**

- 3.5 Effect on Metals: When the remover is tested as specified in 4.5.3 on the metals listed in table I, there shall be no discoloration or evidence of corrosion. Slight discoloration of cadmium plated steel panels shall not be considered objectionable.

TABLE I. Metals for corrosion test

PANEL	RESULT
Aluminum Alloy Alclad 2024 QQ-A-250/5	No visible corrosion
Aluminum Alloy Alclad 7075 QQ-A-250/13	No visible corrosion
Aluminum Alloy 2024 QQ-A-250/4 Anodized per Mil-A-8625	No visible corrosion
Mild Steel Mil-S-7952 Cadmium plated per QQ-P-416	No visible corrosion; slight discoloration
Titanium Alloy 6Al-4V Mil-T-9046	No visible corrosion

Result Conforms

Respectfully submitted,



Patricia D. Viani, SMI Inc.